



# Product datasheet BIOCRYL<sup>®</sup> C

## 1 Identification of the substance / preparation / company

### Product details

Trade name:	BIOCRYL <sup>®</sup> C
Application of the substance / preparation:	Manufacture of dental deep drawing splints
Manufacturer / Supplier:	Scheu Dental GmbH Am Burgberg 20 58642 Iserlohn Germany Tel. 0049 2374 9288-0

## 2 Composition / information on ingredients

### Chemical characterization

CAS-Number:	9011-14-7
Designation:	Polymethylmethacrylat (PMMA)

## 3 Handling and storage

### Handling

Information for safe handling:	When using do not eat, drink or smoke. Provide suction extractors if dust is formed.
--------------------------------	---

### Storage

Storage conditions:	Store dry and dark at max. 20 °C
---------------------	----------------------------------

## 4 Physical, chemical, mechanical and biological properties

### 4.1 General properties

Properties	Guideline	Value
Form	-	Solid
Color	-	transparent or one colored
Odor	-	Odorless
Density	ISO 1183	1,18 g/cm <sup>3</sup>
Water absorption after 24 h at 23 °C	ISO 62 Methode 1	0,3 %

## Product datasheet BIOCRYL® C

### 4.2 Mechanical properties

Properties	Guideline	Value
Tensile strength	ISO 527	70 MPa
Flexional strength	ISO 178	130 MPa
Impact strength 23°C	ISO 179/1eU	20 KJ/m <sup>2</sup>
Notched 23°C	ISO 179/1eA	2 KJ/ m <sup>2</sup>
Yield strain	ISO 527	-
Yield stress	ISO 527	-
Elongation at tear	ISO 527	6 %
E-modulus	ISO 527	3300 MPa
Hardness Shore A	DIN 53505	-
Hardness Shore D	DIN 53505	-
Rockwell Hardness	ISO 2039 H961/30	195

### 4.3 Thermal properties

Vicat softening point	ISO 306 Methode B	103 °C
Thermoform resistance	ISO 75 Methode A	95 °C
	ISO 75 Methode B	100 °C
Continuous stress temperature	ISO 75	-

### 4.4 Biological properties / Biocompatibility

The material has been tested on biocompatibility according to DIN EN ISO 10993. It meets the requirements regarding biological compatibility for medical products / devices.

### 5 Stability and reactivity

#### Thermal decomposition / Conditions to avoid:

No decomposition by intended use.

### 6 Disposal

The material can be recycled after separation or disposed of like commercial or household waste.

The aforementioned data are given most conscientiously but without any obligation. Any processing details are provided merely for guidance: it is the user's responsibility to check the suitability of the product for the intended application.